

Traditional Specifications

Product Name		Trad Silver 18	Trad Silver 30	Trad Bronze 25	Trad Bronze 40
VLT	Single	17%	31%	22%	39%
	Dual	15%	28%	19%	37%
VLR	Single	56%	42%	32%	17%
	Dual	56%	42%	32%	17%
SC	Single	0.23	0.37	0.31	0.47
	Dual	0.36	0.46	0.46	0.58
SHGC	Single	0.20	0.32	0.27	0.41
	Dual	0.31	0.40	0.40	0.50
UV Rej	Single	99.0%	99.0%	99.0%	99.0%
	Dual	99.0%	99.0%	99.0%	99.0%
TSER	Single	80%	68%	73%	59%
	Dual	69%	60%	60%	50%
Glare Red	Single	80%	62%	72%	56%
	Dual	82%	65%	75%	58%

VLT – Visible Light Transmission

VLR – Visible Light Reflection

SC – Shading Coefficient

SHGC – Solar Heat Gain Coefficient

IR Rej – Infrared Rejection

UV Rej – Ultraviolet Rejection

TSER – Total Solar Energy Rejected

Glare Red – Glare Reduction

Performance data is based on this film being applied to the inside of 3mm clear glass. All data calculated using the definitions and equations in ISO9050 & ASHRAE Handbook. The data is subject to variations within industry standards.

Copyright © 2010 Huper Optik® USA (www.huperoptikusa.com) 5821 W. Sam Houston Pkwy. N., Ste. 400, Houston, TX 77041 Phone: 888-296-3456; Fax: 832-467-1190, info@huperoptikusa.com

The data is subject to variations within industry standards.

Copyright © 2010 Huper Optik® USA (www.huperoptikusa.com) 5821 W. Sam Houston Pkwy. N., Ste. 400, H

